

# Declaration of Performance

No. DOP-01-CLA-07 / Page 1 of 2

## Classic Hinge Screws



Material - Carbon Steel (C1022)

Head Type - Reduced

Screw Diameter (mm) - 3.0

We hereby declare these designated products have performed initial type testing under system 3, Annex V of the regulation (EU) no. 305/2011 (Construction Products Regulation), with the reference to the harmonised European standard (hEN) BS EN 14592:2008+A1:2012 (Timber structures - Dowel type fasteners - Requirements) for screws intended for the use in "load bearing timber structures" and produced the calculation/test reports as attached;

The initial type testing has been carried out by independent notified body;  
Strojirensky Zkusebni Ustav, NB # 1015, Hudcova 424/56B, 621 00 Brno-Medlánky, Czechia

Certificate Number: E-30-20008-13

Test Report Number: No. 30-9797/7

Factory Process Control (FPC) has been established by the factory and independently audited by TUV Rheinland UK in accordance with ISO9001.

This declaration of conformity is valid until there is a significant change in the product and declared characteristics. ie. raw material or change in production process.

This declaration is the responsibility of the importer ; T.I.Midwood & Co. Ltd.

Simon Midwood

Managing Director

TIMCO House  
2013

2013

Name

Position

Signature

Location &amp; Date

Test Year

# Declaration of Performance

No. DOP-01-CLA-07 / Page 2 of 2

## Classic Hinge Screws Reduced Head - Ø3.0mm

### Material & Geometry

Material	Carbon Steel (C1022)
Screw diameter (mm)	3.0
Head diameter (mm)	5.08
Inner thread diameter (mm)	2.00

### Mechanical Strength & Stiffness

Characteristic yield moment $M_{y,k}$ at 20° [Nmm] (thread section) in acc. to EN 409	1343
Characteristic withdrawal parameter (loading across the fibre) $f_{ax,k}$ [N/mm <sup>2</sup> ] in acc. to EN 1382 with density of wood $\rho_k = 390\text{kg/m}^3$	17.99
Characteristic withdrawal parameter (loading along the fibre) $f_{ax,k}$ [N/mm <sup>2</sup> ] in acc. to EN 1382 with density of wood $\rho_k = 390\text{kg/m}^3$	12.37
Characteristic head pull-through parameter $f_{tens,k}$ [N/mm <sup>2</sup> ] in acc. to EN 1383 with density of wood $\rho_k = 500\text{kg/m}^3$	56.88
Characteristic tensile capacity $f_{tens,k}$ [kN] in acc. to EN 1383	3.11
Characteristic torsional ratio in acc. to EN 15737 with density of wood $\rho_k = 450\text{kg/m}^3$	6.28

### Durability

Coating (Finish)	Nickel or Yellow coating
Corrosion protection	Service Class 1 acc. to EN 1995-1-1